

NARROWBOAT ANTI-SLIP DECK PAINT

Issue date 09/09/09

PRODUCT DESCRIPTION

Narrowboat Anti-slip deck paint is a high quality 2 hour enamel with added non-slip granules, it offers fast surface drying, good through drying even in thick films, minimum yellowing and outstanding film hardness and toughness.

Narrowboat Anti-slip deck paint is ideal for application to your boat walkways, decks, gunnels and roof sections. It has good resistance to oils and excellent resistance to water, this makes it an ideal choice for use in marine environments. Anti-slip granules provide a resilient non-slip surface to walk on.

Narrowboat Anti-slip deck paint is flexible and also gives good performance over both interior and exterior wood.

COLOUR RANGE

Narrowboat Colour Range, competitor colour ranges are available to order, Joseph Masons, International paints, Blakes, Rylard, Epifanes and Craftmaster. All British Standard Colours: BS; 4800, 2660, 381c. RAL Shades. Any other shade matched by arrangement. Over 20,000 shades

PACKAGING

Available in 1 litre & 2½ litre containers.

HOW TO USE

Brush or Roller

TECHNICAL INFORMATION

SPECIAL PROPERTIES

Solids	Approximately 43 to 55% dependent on colour
Flashpoint	Above 32°C
Specific Gravity	0.90 to 1.12 approximately dependent on colour
Viscosity	1.5 - 3.2 poise ICI Cone And Plate
Temp Resistance	180°C
Storage	12 months in original sealed containers
Touch dry	2 hours
Firm dry	6 hours
Hard dry	12 hours
Thinners	11
Overcoating	wet on wet or after 16 hours
Eqp. Cleaning	White Spirit
Film thickness	100 microns WFT gives approximately 50 microns DFT
VOC	493g/l
See application data	

PREPARATION

Apply over previously primed surface. We recommend Narrowboat HBBP Primer. Use of colour Narrowboat Undercoat will improve coverage and uniformity of Anti-slip deck paint. Surfaces must be thoroughly clean, dry, free from millscale, rust, oil, grease or other contaminants. Use Panel Wipe for removal of oils and greases. For non-ferrous metals, Narrowboat Etch Primer must be used.

APPLICATION

Shake can and then stir thoroughly to ensure granules are evenly distributed within the tin.

Anti-slip deck paint can be brushed or rolled, best results are achieved when applied by roller. Apply one heavy coat then cross roll in opposite direction to obtain an even finish. Ensure paint film is fully cured before walking on.

Application temperatures, avoid applying in very warm weather, remember, panel temperatures may be higher than the air temperature. Air movement will also accelerate drying. Avoid application on very cold or wet days as the risk of blooming (white mist over panels) or loss of gloss may occur.

Recommended number of coats 1 heavy.

**Great British
Paint**



Please note, this product is designed for a single heavy coat application. Recoating may present difficulty with intercoat adhesion. This is due to the 'stippled' nature of the product. It is difficult to adequately sand this finish once it's applied.

Further advice on application is available on the Quick Guide – Repainting your Narrowboat



Please remember to stir our products thoroughly prior to use. For best results shake the tin prior to opening or place upside down to allow any settled pigments do disperse in the tin. Ideally, use a flat edge pallet knife with a minimum of 3/4 inch blade (or similar). Ensure that residues from the bottom of the tin are dispersed throughout. Colour match and product performance will be affected if this product is not thoroughly mixed.

HEALTH AND SAFETY

Refer to health and safety data sheet prior to use.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of Rapidpaint's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO IT'S ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. For Professional Use Only. Ref:25

Technical Data Sheets are also available on our website at www.narrowboatcolours.co.uk



197-199 Bradford Street, Birmingham B12 0JD



Narrowboat Paint Brand is manufactured solely by Rapidpaint

Tel: 0121 693 4020
Fax: 0121 693 5665
Mail: sales@rapidpaint.co.uk

**Great British
Paint**

