

NARROWBOAT HIGH BUILD BRUSHABLE PRIMER (HBBP)

Issue date 09/09/09

PRODUCT DESCRIPTION

Narrowboat HBBP Primer is a high build, easy sandable primer undercoat for use under Narrowboat Undercoats and topcoats.

Narrowboat HBBP Primer is available in two shades of grey and is an excellent basecoat over existing finishes of virtually all types after adequate preparation.

Narrowboat HBBP Primer combines high build and excellent sandability after a short drying period together with excellent application and scratch filling properties.

For satisfactory adhesion to Aluminium and other alloys, the use of Narrowboat Etch Primer is required.

COLOUR RANGE

Light Grey or Charcoal

PACKAGING

Available in 1 litre & 2½ litre containers.

HOW TO USE

Brush, Roller & Spray

TECHNICAL INFORMATION

Solids	Approximately 45% by weight
Flashpoint	Above 32°C
Specific Gravity	1.35 approximately
Viscosity	1 poise ICI Cone And Plate
Temp Resistance	120°C
Storage	12 months in original sealed containers
Touch dry	20 minutes
Firm dry	2 hours
Hard dry	3 hours
Thinners	11 or White Spirit
Overcoating	16 hours min
Eqp. Cleaning	White Spirit
Film thickness	60 microns WFT gives approximately 30 microns DFT
Coverage	16.6 square metres per litre (theoretical)
VOC	414g/l
See application data	

PREPARATION

Narrowboat HBBP Primer can be applied over virtually all sound existing paintwork, also over suitably prepared bare metal, etch primed aluminium and alloys.

APPLICATION

Brush or roller, use straight from the can. The addition of a small amount of white spirit can be used if required. Apply evenly, one coat is usually sufficient over sound, sanded previously painted surfaces. Two coats recommended over bare steel.

Spray: Stir thoroughly, mix with up to 20% of 11 Thinner or White Spirit. Apply 1 light mist coat, followed by 1 full wet coat.

Application temperatures, avoid applying in very warm weather, remember, panel temperatures may be higher than the air temperature. Air movement will also accelerate drying. Avoid application on very cold or wet days.

Further advice on application is available on the Quick Guide – Repainting your Narrowboat



**Great British
Paint**





Please remember to stir our products thoroughly prior to use. For best results shake the tin prior to opening or place upside down to allow any settled pigments do disperse in the tin. Ideally, use a flat edge pallet knife with a minimum of ¼ inch blade (or similar). Ensure that residues from the bottom of the tin are dispersed throughout. Colour match and product performance will be affected if this product is not thoroughly mixed.

HEALTH AND SAFETY

Refer to health and safety data sheet prior to use.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of Rapidpaint's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO IT'S ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. For Professional Use Only. Ref:25

Technical Data Sheets are also available on our website at www.narrowboatcolours.co.uk



197-199 Bradford Street, Birmingham B12 0JD



Narrowboat Paint Brand is manufactured solely by Rapidpaint

Tel: 0121 693 4020
Fax: 0121 693 5665
Mail: sales@rapidpaint.co.uk

**Great British
Paint**

