

NARROWBOAT RED OXIDE METAL PRIMER

Issue Date 09/09/09

PRODUCT DESCRIPTION

Low cost primer for protection of steelwork, with good adhesion and durability, Contains iron-oxide pigments.

COLOUR RANGE

Red Oxide

TECHNICAL INFORMATION

Volume Solids:	50%
Dry Film Thickness:	Typical: 40 microns
Theoretical Coverage:	12.5m ² per litre at 40 microns dry film thickness
Drying Time at 20oC:	Touch Dry: 2 Hours (Will vary with temperature, air movement etc.)
Firm Dry:	4 Hours
Overcoat:	overnight
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5oC to 32oC.
Clean Up:	Narrowboat Thinner R1 or R70.

PACKAGING

1ltr & 2.5litre containers

HOW TO USE

Brush, Roller and Conventional Spray

PREPERATION

Preferred method is abrasive blast. Alternatively, manual clean, chip, scrape and power wirebrush to remove all loose millscale and rust. Any previous coatings remaining must be sound with good adhesion. Feather all edges to achieve smooth profile. Degrease immediately prior to painting using Panel Wipe.

APPLICATION

Ready for use, brush or roller, can be applied over virtually all sound existing paintwork, also over suitably prepared bare metal.

Conventional Spray, may require addition of up to 10% Narrowboat thinner R70 to achieve optimum spray characteristics. Overcoating: May be overcoated with any white spirit based finishes, e.g. Narrowboat Undercoat and Topcoats.

Application temperatures, avoid applying in very warm weather, remember, panel temperatures may be higher than the air temperature. Air movement will also accelerate drying. Avoid application on very cold or wet days.

Further advice on application is available on the Quick Guide – Repainting your Narrowboat



Please remember to stir our products thoroughly prior to use. For best results shake the tin prior to opening or place upside down to allow any settled pigments do disperse in the tin. Ideally, use a flat edge pallet knife with a minimum of 3/4 inch blade (or similar). Ensure that residues from the bottom of the tin are dispersed throughout. Colour match and product performance will be affected if this product is not thoroughly mixed.

**Great British
Paint**



HEALTH AND SAFETY

Refer to health and safety data sheet prior to use.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of Rapidpaint's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO IT'S ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. For Professional Use Only. Ref:25

Technical Data Sheets are also available on our website at
www.narrowboatcolours.co.uk



197-199 Bradford Street, Birmingham B12 0JD

Tel: 0121 693 4020
Fax: 0121 693 5665
Mail: sales@rapidpaint.co.uk



Narrowboat Paint Brand is manufactured solely by Rapidpaint

