

NARROWBOAT UNDERCOAT

Issue date 09/09/09

PRODUCT DESCRIPTION

Narrowboat Undercoat has been formulated for use under Narrowboat Topcoat, and is available in a range of colours complimentary to the topcoat. Narrowboat Undercoat is the preferred undercoat for Narrowboat Topcoat. Using Narrowboat Undercoat will reduce the number of topcoats required for your boat. Narrowboat Undercoat also goes further than topcoat covering approximately 14m² per 1 litre tin.

COLOUR RANGE

Narrowboat Colour Undercoat Chart, any other colour to order.

PACKAGING

1 litre & 2½ litre containers.

HOW TO USE

Brush or Roller

TECHNICAL INFORMATION

Solids	Approximately 50 dependent on colour
Flashpoint	Above 32°C
Specific Gravity	1.30 to 1.50 approximately dependent on colour
Viscosity	2.5 - 3.5 ICI Cone And Plate
Storage	12 months in original sealed containers
Touch dry	3 hours
Firm dry	16 hours
Hard dry	7 days
Thinners	11 or White Spirit
Overcoating	6 hours minimum, maximum indefinite
Eqp. cleaning	White Spirit
Film thickness	70 microns WFT gives approximately 30 microns DFT
Coverage	14 square metres per litre (theoretical)
VOC	390g/l approximately

See application data

PREPARATION

Apply over suitably prepared primer or sound old paint finish, we recommend Narrowboat High Build Brushable Primer or Narrowboat Red Oxide Primer.

APPLICATION

Apply with either roller or brush, one coat is normally sufficient. For best results apply evenly in 3ft sections and lay off using a lightly loaded brush, light downward strokes from top to bottom in one stroke. Up to 10% Thinner 11, PPA or White Spirit may be added to ease application if required. Once through dry lightly sand prior to topcoat application.

Application temperatures, avoid applying in very warm weather, remember, panel temperatures may be higher than the air temperature. Air movement will also accelerate drying. Avoid application on very cold or wet days.



Further advice on application is available on the Quick Guide – Repainting your Narrowboat



Please remember to stir our products thoroughly prior to use. For best results shake the tin prior to opening or place upside down to allow any settled pigments to disperse in the tin. Ideally, use a flat edge pallet knife with a minimum of ¼ inch blade (or similar). Ensure that residues from the bottom of the tin are dispersed throughout. Colour match and product performance will be affected if this product is not thoroughly mixed.

**Great British
Paint**



NARROWBOAT UNDERCOAT

Issue date 09/09/09

HEALTH AND SAFETY

Refer to health and safety data sheet prior to use.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of Rapidpaint's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO IT'S ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. For Professional Use Only. Ref:25

Technical Data Sheets are also available on our website at
www.narrowboatcolours.co.uk



197-199 Bradford Street, Birmingham B12 0JD

Narrowboat Paint Brand is manufactured solely by Rapidpaint

Tel: 0121 693 4020
Fax: 0121 693 5665
Mail: sales@rapidpaint.co.uk

