

NARROWBOAT TOPCOAT

Issue date 08/09/09

PRODUCT DESCRIPTION

Narrowboat Topcoat is a traditional ultra high quality, high solids synthetic enamel for both brush and roller application. Narrowboat Topcoat gives an extra long wet edge time allowing the largest of boats to be brushed or rolled without brush drag. Narrowboat Topcoat gives ultimate high gloss, build and scratch filling combined with excellent water resistance, flexibility and excellent exterior durability and toughness.

Narrowboat Topcoat is highly pigmented giving excellent covering power. Narrowboat Topcoat contains non-aggressive solvents making it the ideal choice over existing paint surfaces. The quality of the Narrowboat Topcoat allows longer maintenance intervals extending life between repaints. High quality, high gloss, long wet edge for brushing and a very durable coating.

COLOUR RANGE

Narrowboat Colour Range, competitor colour ranges are available to order, Joseph Masons, International paints, Blakes, Rylard, Epifanes and Craftmaster. All British Standard Colours: BS; 4800, 2660, 381c. RAL Shades. Any other shade matched by arrangement. Over 20,000 shades

PACKAGING

1 litre & 2½ litre containers.

HOW TO USE

Brush or Roller

TECHNICAL INFORMATION

Solids	Approximately 50 to 65% dependent on colour
Flashpoint	Above 32°C
Specific Gravity	0.91 to 1.30 approximately dependent on colour
Viscosity	3.6 poise ICI Cone and Plate
Temp Resistance	90°C
Storage	12 months in original sealed containers
Colour retention	Excellent
Touch dry	4 hours
Firm dry	16 hours
Hard dry	2 days
Thinners	THINNER 11
Overcoating	16 hours minimum
Eqp. Cleaning	White Spirits
Film thickness	100 microns WFT gives approximately 50 microns DFT
Coverage	10 square metres per litre (theoretical)
VOC	390g/l
See application data	

PREPARATION

Narrowboat Topcoat may be used over a wide variety of surfaces which have been suitably sanded, primed and undercoated. We recommend Narrowboat High build Primer and then Narrowboat Undercoat.

Narrowboat Topcoat can be applied directly to Narrowboat High Build Primer, however, coverage of the Topcoat will be reduced.

APPLICATION

Narrowboat Topcoat is ideally applied by brush or roller in 3ft sections and layed off using a lightly loaded brush, light downward strokes from bottom to top of panel in one stroke. Narrowboat Topcoat is formulated for excellent brushability. Small amounts of Narrowboat Thinner 11, PPA or white spirit can be added to further improve wet edge and brushability over larger panel areas.

De-nib between coats with fine abrasive 400g-500g machine, 600g wet'n'dry.



NARROWBOAT TOPCOAT

Application temperatures, avoid applying in very warm weather, remember, panel temperatures may be higher than the air temperature. Air movement will also accelerate drying. Avoid application on very cold or wet days as the risk of blooming (white mist over panels) or loss of gloss may occur.

Recommended number of coats 2

Further advice on application is available on the Quick Guide – Repainting your Narrowboat



Please remember to stir our products thoroughly prior to use. For best results shake the tin prior to opening or place upside down to allow any settled pigments do disperse in the tin. Ideally, use a flat edge pallet knife with a minimum of 3/4 inch blade (or similar). Ensure that residues from the bottom of the tin are dispersed throughout. Colour match and product performance will be affected if this product is not thoroughly mixed.

HEALTH AND SAFETY

Refer to health and safety data sheet prior to use.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of Rapidpaint's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO IT'S ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. For Professional Use Only. Ref:25

Technical Data Sheets are also available on our website at
www.narrowboatcolours.co.uk



197-199 Bradford Street, Birmingham B12 0JD



Narrowboat Paint Brand is manufactured solely by Rapidpaint

Tel: 0121 693 4020
Fax: 0121 693 5665
Mail: sales@rapidpaint.co.uk

